

**Non-linear piezoelectric properties of the thin $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) films
deposited on the Si-substrate**

J.Nosek¹, M.Sulc¹, L.Burianova¹, C.Soyer², E.Cattan², D.Remiens²

¹Technical University Liberec, International Center for Piezoelectric Research, Halkova 6,
CZ-461 17 Liberec 1, Czech Republic, e-mail: jaroslav.nosek@vslib.cz

²Université de Valenciennes, IEMN – DOAE - MIMM, F-59600 Maubeuge, France

Abstract

In this paper some non-linear piezoelectric properties are investigated in lead zirconate-titanate $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) thin films, sputtered on the Si/SiO₂/Ti/Pt substrates. The thin PZT films were optimised by technology conditions (sputtering, $(\text{Zr}_x\text{Ti}_{1-x})$ composition, PZT film thickness, buffer and seeding layers thickness). The significant piezoelectric response for PZT(60/40) rhombohedral compositions, (111) orientations and thickness of 1.02 to 2.2 μm has been observed. The effective piezoelectric coefficient $d_{33} = 225$ pC/N was found for high electric field of 10 MV/m. The non-linear piezoelectric response, depending on electric field, frequency and temperature, was studied experimentally using an original double-beam laser interferometer and an optical cryostat. The temperature dependence of the thickness strain was investigated by laser interferometer in the temperature range – 33 °C to 57 °C.

The $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ - Si/SiO₂/Ti/Pt samples were prepared in the University of Valenciennes (France), and measured in the Laboratory of laser interferometry at the Technical University of Liberec (Czech Republic).

Keywords: A. Films, C. Piezoelectric properties, D. PZT, E. Actuators, Laser interferometry.

1. Introduction

It is well known that the thin and thick lead zirconate-titanate $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) films are of major interest in the actuation of active structures in micro-electromechanical systems (MEMS) of miniaturised functionality. Because the small thickness of the PZT films results in a high electric field, the non-linear phenomena must be considered both in the design of micro-electromechanical circuit and in the function of the PZT electromechanical system.¹

To create a Si- based micro-electromechanical system, some technologies as hybrid - or thin film technologies based on the low-pressure chemical vapour deposition (LPCVD), sputtering, and sol gel techniques are used.² One of these technologies, i.e. the RF sputtering³, was used so that a ferroelectric $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) thin film on the Si substrate could be obtained.^{4,5} The piezoelectric properties of the PZT thin films, namely of (111) and (100) orientations⁶, have been extensively studied by many laboratories.^{7,8,9} It is obvious that thin films that are clamped to a substrate, differ from bulk ceramics in microstructure and properties.^{10,11}

In the last paper, we described the experimental investigation of the PZT (45/55), PZT(60/40), (110) and (111) orientations of the thin films.¹² The aim of this paper is to give an account of the investigation of the piezoelectric response of the $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ - Pt/Ti/SiO₂/Si structures such as PZT(60/40), (111) orientation, depending on the technology of preparation, activated electric field, frequency and temperature. The effective piezoelectric coefficients d_{33} of the PZT thin film were determined by piezoelectric induced displacement measured on the thin film sample using the double beam laser interferometer and optical cryostat.¹³ The experimentally obtained data are important for verification of some non-linear models of non-linear behaviour of PZT thin film properties.¹⁴

2. Samples preparation

The 1,02 μm – 2.2 μm thick PZT thin films were grown by RF magnetron sputtering using the metallic targets of Pb, Ti and Zr.^{3,4,5} The Zr/Ti ratio was obtained by changing the powers on the different metallic targets. The rhombohedral PZT (60/40) thin films were created and used for measurements. The preferential orientation (texture) (111) was determined with a X-Ray diffractometer. The sequence for the (111) orientation was: PZT (111)/Pt (200 nm)/TiO₂ (2nm)/Ti (100 nm)/ TiO₂/SiO₂ (300 nm)/ Si substrate (380 μm). On Pt, (111) orientation was obtained by means of a Pt (111) bottom electrode and the TiO₂ seeding layer. A gold layer was deposited on the back of the substrate to optimise the laser beam reflection. The PZT films were annealed at 625°C for 30 min. The parameters of the sputtering are given in Table 1.

Table 1

A set of measured PZT thin film samples is shortly described in Table 2.

Table 2

3. Experimental procedure

The piezoelectric-induced thickness displacements of PZT layers were performed with a very sensitive double-beam laser interferometer in the temperature range of –33 °C to 57 °C. Based on the He-Ne laser (SIOS model SL03), the Mach-Zehnder double beam interferometer connected to the optical helium cryostat Oxford Instruments, Inc. was designed in our laboratory.^{13,15}

Fig.1

To eliminate the vibrations of cooling system caused by the helium pump, our interferometer was miniaturised¹⁵ and situated in the optical head of the cryogenic system. Because the interferometer is very small and compact, the placement inside the optical head of cryostat

suppressed the amplitude of vibration of optical elements in the interferometer. Motion of these elements only shifted the interference pattern that remained stable. This technical solution also helped to solve the problem of temperature stability. The thermal shift of optical elements (due to non-homogenous temperature field) and the change of elements length were compensated by the feedback. The interference pattern is transmitted to the photodiode and the signal response from the preamplifier is measured with a digital lock-in (Stanford Research SR-830). The samples in the cryostat were cooled to the chosen temperature and stabilised at this temperature for 10 minutes. For measurements, the cryostat system was switched off to eliminate sample vibrations of mechanical causes. Under this condition, the piezoelectric response, such as strain, displacement and coefficients d_{33} vs. temperature, frequency, and electric field, were measured.

4. Results and discussion

With the aid of the basic formula for thickness displacement Δ ($\Delta = d_{33} V_m$), the effective piezoelectric coefficients d_{33} of all samples were determined after poling them by electric field 20 MV/m within 20 min. On the Fig.2, for rhombohedral PZT (60/40), (111) sample #39 one can observe a frequency dependence of the piezoelectric response for variable time after poling. Small increase or small changes of the d_{33} (about 120 pC/N) are characteristic for the time delays of 60 to 1100 min after poling. The frequency of the driving electric field $E = E_o \sin(\omega t)$ changes from 200 Hz to 2 kHz. The temperature dependence (Fig.3) of the strain, induced by electric field ($E_o = 8.31$ MV/m) changes between 160×10^{-6} and 240×10^{-6} (sample #39, 2 min after poling).¹² This value is smaller than the value of the bulk PZT ceramics. Coefficient d_{33} decreases with decreasing temperature, but this decrease is not so strong as in case of the bulk samples.¹¹

Fig. 3

Fig. 4

The Fig. 4 shows the non-linear dependence of the thickness displacement (in nm) on varying DC electric field (PZT (60/40), (111), sample #1). It is clear that the determination of the threshold field¹ is probably less precise and must be studied in detail. The displacement vs. field (and $d_{33}(E)$ dependence) increases quasi-linearly. At higher field (more of 8.0 MV/m) the displacement (and $d_{33}(E)$) becomes constant due to the saturation. The value of electric field, where saturation was observed, is about 8-10 MV/m. These values correspond to the displacements of 4 nm. It is a similar value to the values that have been published before (on 300 nm thin PZT layers¹¹).

The PZT (60/40) sample # 1 was investigated in high electric fields (0 – 15 MV/m) and the strain-field dependencies are presented in the Figs. 5 and 6. Fig.5 shows the effective d_{33} coefficient as a function of the applied voltage, sample before poling. The bias voltage is ± 10 V of the triangle shape, 1 mHz bias frequency, sample #1.

Fig.5

Fig.6

The influence of the high electric field has been demonstrated. If the applied electric field is higher than the coercive field in the PZT film (averaged coercive field ≈ 6.8 MV/m for sample #1), ferroelectric domains start to switch. Therefore, the butterfly-type strain hysteresis loop has been observed. This phenomena was reported also by Kholkin et al.⁶ Our experiment shows an influence of the poling by a triangle shaped voltage of ± 15 V ($E_0 = 8.82$ MV/m). In this case, the typical butterfly-type strain hysteresis loop is quasi-symmetric due to the high electric field,

which is significant for poling (Fig.6). The observed effective piezoelectric coefficient d_{33} is about 225 pC/N. This value is in contradiction with ⁸, where the rhombohedral PZT (60/40), (111) oriented thin film shows smaller values. According to the data published in ⁶ for the low applied field, one can observe that interferometer response follows the driving field. This is a case of the pure piezoelectric effect. In low electric field, the strain-field dependencies are quasi-linear.

This begs an interesting question for a discussion about the possibility of determination both intrinsic and extrinsic contributions to the piezoelectric response of the thin PZT layer. ²

It is known that created 180^0 domain wall motion does not involve mechanical strain. Therefore, moving 180^0 domains contribute only to the dielectric constant ϵ but not to the d_{33} . We suggest that for ideally (111) oriented films also the 90^0 domain contribution does not produce any mechanical strain, which is in agreement with ¹. The non-linear behaviour of d_{33} may give useful information on the relative role of 180^0 and non- 180^0 domain wall processes in PZT thin films.

Conclusions

The technology conditions of rhombohedral PZT (60/40) thin film sputtered on the Si / SiO₂ /Ti/Pt substrate were optimised so that the (111) texture could be obtained. The non-linear piezoelectric response depending on electric field, frequency, and temperature was studied experimentally using a double beam laser interferometer and an optical cryostat.

The piezoelectric response as $d_{33} = 250$ pC/N was found for above-mentioned samples of the thickness 1.7 μm . The temperature dependencies of piezoelectric coefficient d_{33} were measured in the temperature range of -33 °C to 57 °C.

Acknowledgments

This research was supported in part by Ministry of Education of the Czech Republic, grant code MSM 242200002.

References

1. Kholkin, A., Non-linear piezoelectric response in lead zirconate-titanate (PZT) films, *Ferroelectrics*, 2000, **238**, 799-807.
2. Setter, N.: *Piezoelectric Materials in Devices*, Ceramics Laboratory, EPFL Lausanne, 2002, Switzerland, ISBN 2-9700346-0-3.
3. Velu, G., Remiens, D. and Thierry, B., Ferroelectric properties of PZT thin films prepared by sputtering with stoichiometric single oxide target: Comparison between conventional and rapid thermal annealing, *J.Europ.Ceram.Soc.* 1997, **17**, 1749-1755.
4. Soyer, C., Cattan, E., Remeins, D., Guilloux-Viry M., Ion beam etching of lead-zirconate-titanate thin films: Correlation between etching parameters and electrical properties evolution, *J. Appl. Phys.*, 2002, **92**, 1048-1055.
5. Soyer, C., Hackart, T., Cattan, E., Remiens, D., (Zr/Ti) ratio effect on RF magnetron sputtered lead titanate zirconate films. *Integrated Ferroelectrics*, 2001, **35**, 1959-1968.
6. Taylor, D.V., Damjanovic D., Piezoelectric properties of rhombohedral $\text{Pb}(\text{Zr},\text{Ti})\text{O}_3$ thin films with (100), (111) and „random“ crystallographic orientation. *Appl.Phys.Letters*, 2000, **76**, 12, 1615-1617.
7. Kholkin, A.L., Wutchrich, Ch., Taylor, D.V., and Setter, N., Interferometric measurements of electric-field induced displacements in piezoelectric thin films, *Rev.Sci.Instrum.*, 1996, **67**, 5, 1935-1941.

8. Du, X. H., Zheng, J., Belegundu, U., and Uchino, K., Crystal orientation dependence of piezoelectric properties of lead zirconate titanate near the morphotropic phase boundary. *J. Appl. Phys. Letters*, 1998, **72**, 19, 2421-2423.
9. Pan, W.Y., Wang, H., Cross, L.E., and B.R.Lee, Double beam laser interferometer measurements of surface displacements at the resonance frequencies of PZT piezoelectric ceramic resonators. *Ferroelectrics*, 1991, **120**, 231-239.
10. Barzegar, A., Damjanovic, D., Ledermann, N., and Muralt, P., Piezoelectric response of thin films determined by charge integration technique: substrate bending effects. *J. Appl. Phys.*, 2003, **93**, 8, 4756-4760.
11. Hiboux, S., Muralt, P., Piezoelectric and dielectric properties of sputter deposited (111), (100) and random-textured $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) thin films. *Ferroelectrics*, 1999, **224**, 315-322.
12. J.Nosek, L.Burianova, M. Sulc, C.Soyer, E.Cattan, D. Remiens, About the measurements of the d_{33} piezoelectric coefficient of the PZT film-Si/SiO₂/Ti/Pt substrates using an optical cryostat. *Ferroelectrics* 2003, **292**, 103-109.
13. Šulc, M., Burianová, L., Nosek, J., On the precision of the new laser interferometer in a wide temperature range. *Ann. Chim. Sci. Mat.* 2001, **26**, 43-48.
14. Walter, V., Delobelle, P., Le Moal P., A nonlinear electromechanical model for ferroelectric materials: application to soft-PZT thick films screen-printed on alumina substrate. *IEEE Trans. Ultrason., Ferroel., Freq. Control*, 2003, **50**, 5, 471-480.
15. Sulc, M., Laser interferometer for measurement of piezoelectric induced displacement. Czech Patent No. CZ9904400 A (1999).

Caption page for tables:

TABLE 1 Conditions of sputtering depositions of PZT thin films.

TABLE 2 Measured $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ thin film samples.

TABLE 1 Conditions of the sputtering depositions of PZT thin films

Target diameter	76,2 mm
RF power density	2,36 W/cm ²
Target-substrate distance	60 mm
Working pressure	30 mtorr
Substrate temperature	25 °C - 160 °C

TABLE 2 Measured $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ thin film samples

Sample	Zr _x	Thickness	Preferentially orientation
# 1	0.60	1.0 μm	(111)
# 2	0.60	1.9 μm	(111)
# 3	0.60	2.2 μm	(111)
# 39	0.60	1.7 μm	(111)

Note:

C₀ as static capacity measured between top electrodes and bottom electrode varies from 4.11 nF to 4.78 nF for sample #1. Corresponding permittivity is about 675. The typical diameter of each of top electrodes is 1 mm.

The samples #1, #2 and #3 were delivered in 2003, sample # 39 in 2002, both from University of Valenciennes (France).

Caption page for figures:

Fig. 1 Schematic drawing of double beam interferometer for measurement inside of cryostat chamber.

Fig. 2 Frequency dependency of d_{33} coefficient for PZT thin layer, measured at delay times 2 min, 60 min, 130 min and 1100 min after poling, sample #39.

Fig.3 Temperature dependence of strain for PZT thin layer, frequency of applied field 1000 Hz, 10 V_{ef}, sample #39.

Fig.4 Piezoelectric induced displacement vs. DC electric field, poled sample #1.

Fig.5 Effective d_{33} coefficient as a function of the applied voltage, before poling, bias ± 10 V of the triangle shape, 1 mHz bias frequency, sample #1.

Fig.6 Effective d_{33} coefficient as a function of the applied voltage, after poling, bias ± 15 V of triangle shape, 1 mHz bias frequency, sample #1.




Fig.1 Schematic drawing of the double beam interferometer for measurement inside of helium cryostat chamber.




Fig.2 Frequency dependency of d_{33} coefficient for PZT thin layer, measured at delay times 2 min, 60 min, 130 min and 1100 min after poling, sample #39.




Fig.3 Temperature dependence of strain for PZT thin layer, frequency of applied field 1000 Hz, 10 V_{ef}, sample #39.




Fig.4 Piezoelectric induced displacement vs.DC electric field, poled sample #1.




Fig.5 Effective d_{33} coefficient as a function of the applied voltage, before poling, bias ± 10 V of the triangle shape, 1mHz bias frequency, sample #1.




Fig.6 Effective d_{33} coefficient as a function of the applied voltage, after poling, bias ± 15 V of the triangle shape, 1 mHz bias frequency, sample #1.

Electroceramics IX - 2004

Cherbourg, 31 May – 3 June 2004

Paper Length Form

Abstract No.: 337

Title: Non-linear piezoelectric properties of the $\text{Pb}(\text{Zr}_x\text{Ti}_{1-x})\text{O}_3$ (PZT) films

Authors: J.Nosek, L.Burianova, C.Soyer, E.Cattan, D.Remiens

Calculation:

Item:	Template:	Calculation:
Title:	60 + 20 x (no. of lines of text in title) + 20 x (no. of lines of authors) + 10 x (no. of lines of address)	60 $20 \times 2 = 40$ $20 \times 1 = 20$ $10 \times 3 = 30$ Subtotal 150
Abstract:	+ 0.5 x (no. of words in abstract) + 40	$0,5 \times 164 = 82$ +40 Subtotal 122
Main Text:	+ 0.5 x (no. of words) + 20	$(0,5 \times 1394) + 20 = 717$
Headings:	+ 20 x (no. of headings (excepted of abstract))	$20 \times 6 = 120$
Figures:	+ (height figure 1 (in mm when 80 mm wide)+ 20) + (height figure 2 + 20) etc.... (NB: x 2 when table straddles 2 columns)	$420 + 120 = 540$ (6 Figures)
Tables:	+ (height table 1 [4 x no. of lines] + 30) + (height table 1 [4 x no. of lines] + 30) etc.... (NB: x 2 when figure straddles 2 columns)	$(4 \times 5) + 30 = 50$ $(4 \times 5) + 30 = 50$ Subtotal 100
Formulas:	+ 15 x (no. of formula)	
References:	+ 12 x (no. of references)	$12 \times 15 = 180$
Total:	=	1929
No. of Pages:	<u>Total</u> = no. of pages/470	$1929/470 = 4.1$

The result of this calculation for your paper should fall into one of the following bands:

3.6-4.0 for a 4-page article (regular contribution)

5.6-6.0 for a 6-page article (invited contribution)

7.6-8.0 for an 8-page article (plenary contribution)

A paper that is not within these ranges is likely to produce a blank space or page in the journal.